## RESEARCH PROJECT

# UTILIZATION OF NANOMATERIAL WITH CUBIC MESOSTRUCTURE TO INCREASE EFFICIENCY OF ENZYMATIC CONVERSION OF CELLULOSE INTO GLUCOSE



## Submitted by:

Kevin Indrawan Sucipto NRP: 5203012015 Christian Harmoko NRP: 5203012023

DEPARTMENT OF CHEMICAL ENGINEERING FACULTY OF ENGINEERING WIDYA MANDALA CATHOLIC UNIVERSITY SURABAYA 2015

#### LETTER OF APPROVAL

The research entitled:

Utilization of Nanomaterial with Cubic Mesostructure to Increase Efficiency of Enzymatic Conversion of Cellulose into Glucose Which was conducted and submitted by:

Name: Christian Harmoko

NRP : 5203012023

Has been approved and accepted as progress report for one of requirement for Bachelor Engineering degree in Chemical Engineering Department, Faculty of Engineering, Widya Mandala Surabaya Catholic University by following supervisor/s.

Supervisor

Sandy Budi Hartono, Ph.D.

521.99.0401

Surabaya, 15 June 2015

Co-Supervisor

Ery Susiany R, ST., MT.

521.98.0348

The Committees

Chairman

Ir Survadi Ismadji, Ph.D.

521.93.0198

Member

Antaresti, ST, M.Eng.Sc,

521 99 0396

Secretary

Sandy Budi Hartono, Ph.D.

521.99.0401

Member

Dr. Ir. Suratno. L, MS.

521.87.0127

Dean of Engineering Faculty

Survadi Ismadji, Ph.D

521 93.0198

Authorized by Willy Head of Chemical Engineering Department

Wendy Irawaty, Ph.D.

\$2197.00 kg

## LETTER OF APPROVAL

The research entitled:

Utilization of Nanomaterial with Cubic Mesostructure to Increase Efficiency of Enzymatic Conversion of Cellulose into Glucose Which was conducted and submitted by:

Name: Kevin Indrawan Sucipto

NRP : 5203012015

Has been approved and accepted as progress report for one of requirement for Bachelor Engineering degree in Chemical Engineering Department, Faculty of Engineering, Widya Mandala Surabaya Catholic University by following supervisor/s.

Surabaya, 15 June 2015 Co-Supervisor Supervisor Ery Susiany R, ST., MT. Sandy Budi Hartono, Ph.D. 521.98.0348 521.99.0401 The Committees Secretary Chairman Sandy Budi Hartono, Ph.D. Ir. Saryadi Kapadi 521.99.0401 521.93.0198 Member Membe Dr. Ir. Suratno. L, MS. Antaresti, ST, M.Eng.Sc, 521.87.0127 9.0396 Authorized by hemical ng Faculty Department

#### COPY RIGHT AGREEMENT

In order to support the development of science and technology, I am as the student of Widya Mandala Surabaya Catholic University:

Name: Christian Harmoko

Student ID: 5203012023

Agree to transfer the copyright of my thesis/paper:

Title:

Utilization of Nanomaterial with Cubic Mesostructure to Increase Efficiency of Enzymatic Conversion of Cellulose into Glucose

To be published in internet or other media (Digital Library of Widya Mandala Surabaya Catholic University) for academic purpose according to copyright law in Indonesia

Surabaya,

Author



Christian Harmoko 5203012023

#### COPY RIGHT AGREEMENT

In order to support the development of science and technology, I am as the student of Widya Mandala Surabaya Catholic University:

Name: Kevin Indrawan Sucipto

Student ID: 5203012015

Agree to transfer the copyright of my thesis/paper:

Title:

Utilization of Nanomaterial with Cubic Mesostructure to Increase Efficiency of Enzymatic Conversion of Cellulose into Glucose

To be published in internet or other media (Digital Library of Widya Mandala Surabaya Catholic University) for academic purpose according to copyright law in Indonesia

Surabaya,

Author



Kevin Indrawan Sucipto 5203012015

## LETTER OF DECLARATION

I declare that this research was my own work and does not contain any material that belongs to the others, unless it was stated in the references. Should it is known that his research belongs to others. I aware and accept the consequences that his research cannot be used as a requirement to achieve a **Bachelor of Engineering** degree

Surabaya,

Student,



Christian Harmoko 5203012023

## LETTER OF DECLARATION

I declare that this research was my own work and does not contain any material that belongs to the others, unless it was stated in the references. Should it is known that his research belongs to others. I aware and accept the consequences that his research cannot be used as a requirement to achieve a **Bachelor of Engineering** degree

Surabaya,

Student,



Kevin Indrawan Sucipto 5203012015

# TABLE OF CONTENTS

RESEARCH F	PROJECTi
LETTER OF A	APPROVALii
LETTER OF A	APPROVALiii
COPY RIGHT	AGREEMENTiv
COPY RIGHT	AGREEMENTv
LETTER OF I	DECLARATIONvi
LETTER OF I	DECLARATIONvii
TABLE OF CO	ONTENTSviii
TABLE OF FI	GURExi
LIST OF TAB	LExii
PREFACE	xiv
ABSTRACT	xv
CHAPTER I	1
I.1	Background
I.2	Objective2
CHAPTER II.	3
II.1	Cellulose Material
II.2	Cellulase
II.3	Enzymatic Conversion of Cellulose to Glucose5
II.4	Porous Silica Material as Enzyme Carrier7
II.5	Mesoporous Silica Materials8
II.6	Surface Functionalization

	II.7	Previou	s Studies	on	Cellulase	Enzyme	Immobilization
		within 1	Mesoporou	s Sili	ca Materia	ıls	11
	II.8	Charac	erization N	1etho	od		13
СНАРТЕ	ER III		•••••				15
	III.1	Chemic	als				15
	III.2	Instrum	ents				16
	III.3	Researc	h Design				17
	III.	3.1 R	esearch Sc	heme	e		17
	III.	3.2 V	Vork Schen	ne			18
	III.	3.3 R	ecycle of F	Enzyr	natic Nanc	porous Si	lica19
	III.4	Variabl	es				19
	III.	4.1 D	ependent V	/aria	bles		19
	III.	4.2 II	ndependent	Vari	ables		19
	III.5	Researc	h Methodo	ology			20
	III.	5.1 S	ynthesis of	Nan	oporous Si	lica	20
	III.	5.2 N	Iethanol Ex	ktract	ion		20
	III.				•		ermine Enzyme20
	III.				•	•	Reusability of
	III.6	Analyz	e Method				22
	III.7	Researc	h Schedule	·			23
СНАРТЕ	R IV						24

	IV.1	Vinyl-functionalized mesoporous silica with Large Pore	24
	IV.2	Enzyme Immobilization	32
	IV.3	Activity	37
	IV.4	Stability and Reusability	43
CHAPTI	ER V		46
	V.1	Conclusion	46
	V.2	Suggestion	46
REFERE	ENCES	S	47
APPENI	OIX A		50
APPENI	OIX B		51
APPENI	DIX C		52
APPENI	DIX D		53
APPENI	DIX E		54
APPENI	OIX F.		56
APPENI	OIX G		58
APPENI	OIX H		64
APPENI	OIX I		70
APPENI	OIX J .		81
APPENI	OIX K		82
APPENI	DIX L		93
APPENI	OIX M	[	94
ADDENIT	N XIO		07

# TABLE OF FIGURE

	Figure II.I The Diagram of Cellulosic Ethanol Production by Iog	en
Corpo	pration <sup>8</sup>	6
	Figure II.II Mesoporous Silica Synthesis	8
	Figure II.III SEM Images of SBA-15 <sup>11</sup> (A) and FDU-12 <sup>12</sup> (B)	9
	<b>Figure II.IV</b> TEM Images of FDU-12 <sup>12</sup> (A) and SBA-15 <sup>11</sup> (B)	9
	<b>Figure II.V</b> Structure of FDU- $12^{18}$ (A) and SBA- $15^{20}$ (B)	10
	Figure III.I Research Scheme	17
	FigureIII.II Work Scheme	18
	Figure III.III Recycle of Enzymatic Nanoporous Silica	19
	Figure IV.I Nitrogen sorption isotherms of NS-pure	26
	Figure IV.II Nitrogen sorption isotherms of MS-pure	27
	Figure IV.III FTIR spectra result of MS	29
	Figure IV.IV FTIR spectra result of NS.	30
	Figure IV.V TEM result (A) MS-pure (B) NS-pure	32
	Figure IV.VI Adsorption Isotherms of cellulose on MS	35
	Figure IV.VII Adsorption Isotherms of cellulose on NS	36
	Figure IV.VIII Loading and activity result from Hartono	41

# LIST OF TABLE

Table A. 1. Dilution of BSA	. 55
Table A. 2. Dilution of glucose	. 57
Table A. 3. Table of C <sub>o</sub> MS-pure	. 59
Table A. 4. Table of C <sub>0</sub> MS-V <sub>5</sub>	. 59
Table A. 5. Table of C <sub>0</sub> MS-V <sub>10</sub>	. 60
Table A. 6. Table of C <sub>o</sub> MS-V <sub>20</sub>	. 60
Table A. 7. Table of C <sub>o</sub> NS-pure	.61
Table A. 8. Table of C <sub>0</sub> NS-V <sub>5</sub>	.61
Table A. 9. Table of C <sub>0</sub> NS-V <sub>10</sub>	. 62
Table A. 10. Table of C <sub>0</sub> NS-V <sub>20</sub>	. 62
Table A. 11 Table of C <sub>o</sub> MS-non extraction	. 63
Table A. 12. Table of C <sub>o</sub> NS-non extraction	. 63
Table A. 13. Table of C <sub>t</sub> MS-pure	. 65
Table A. 14. Table of C <sub>t</sub> MS-V <sub>5</sub>	. 65
Table A. 15. Table of C <sub>t</sub> MS-V <sub>10</sub>	. 66
Table A. 16. Table of C <sub>t</sub> MS-V <sub>20</sub>	. 66
Table A. 17. Table of C <sub>t</sub> NS-pure	. 67
Table A. 18. Table of C <sub>t</sub> NS-V <sub>5</sub>	. 67
Table A. 19. Table of C <sub>t</sub> NS-V <sub>10</sub>	. 68
Table A. 20. Table of C <sub>t</sub> NS-V <sub>20</sub>	. 68
Table A. 21. Table of C <sub>t</sub> MS-non extraction	. 69
Table A. 22. Table of C <sub>t</sub> NS-non extraction	. 69
Table A. 23. Table of qe MS-pure	.71
Table A. 24. Table of q <sub>e</sub> MS-V <sub>5</sub>	.72
Table A. 25. Table of q <sub>e</sub> MS-V <sub>10</sub>	.73
Table A. 26. Table of q. MS-V <sub>20</sub> .	.74

Table A. 27.	Table of qe NS-pure	75
Table A. 28.	Table of qe NS-V5	76
Table A. 29.	Table of $q_e$ NS-V <sub>10</sub>	77
Table A. 30.	Table of $q_e$ NS-V <sub>20</sub>	78
Table A. 31.	Table of q <sub>e</sub> MS-non extraction	79
Table A. 32.	Table of qe NS-non extraction	80
Table A. 33.	Table of activity MS-pure	85
Table A. 34.	Table of activity MS-V <sub>5</sub>	86
Table A. 35.	Table of activity MS-V <sub>10</sub>	87
Table A. 36.	Table of activity MS-V <sub>20</sub>	88
Table A. 37.	Table of activity NS-pure	89
Table A. 38.	Table of activity NS-V <sub>5</sub>	90
Table A. 39.	Table of activity NS-V <sub>10</sub>	91
Table A. 40.	Table of activity NS-V <sub>20</sub>	92
Table A. 41.	Table of Free Enzyme Test	93
Table A. 42.	Table of Stability	95
Table A. 43.	Table of Reusability	97

#### **PREFACE**

First of all, thanks to God for his grace and love so the writer can finish this report on time. This report is presented to fulfill one of the requirements in accomplishing the Bachelor Degree at the Department of Chemical Engineering in Widya Mandala Catholic University. The writer would like to express his sincere gratitude to the following:

- Mr. Sandy Budi Hartono and Mrs. Ery Susiany as my supervisors who guide me in writing this thesis report and give motivation and advice in the experiments.
- 2. The examiners who give suggestions and critics in this reports.
- 3. My family and friends who give me never ending supports.
- 4. Anyone that can't be mentioned directly or indirectly who has helped the writer in completing this script. The writer does appreciate any opinion and suggestion for the improvement of this thesis report.

#### ABSTRACT

The use of conventional fuel becomes major part of life that can't be separate anymore. However, conventional fuel can't be renewable so over time the stocks are dwindling and cause fuels price has been increase. Recently, Indonesia has changed to become one of petroleum importing countries. It makes the country economic more vulnerable against rising fuel prices. Availability of alternative fuels such as bio-ethanol or bio-diesel becomes very important.

To overcome this challenges, alternative fuel researches are encouraged by so many countries. One of organic component that can be used as a raw material to produce bio-ethanol is cellulose. Cellulose is the largest organic material in earth. Cellulose can be easily founded from agricultural residue such as corn head. Cellulose can be converted to glucose which is the base material to produce bio-ethanol.

There are two processes to convert cellulose into glucose: through chemical process and enzymatic process. Cellulase enzymes convert cellulose materials into glucose. The enzymatic process have a benefit, the high cellulose conversion into glucose and zero waste process as compared to chemical process. Yet, the enzymatic process is hindered due to the high cost of enzyme production. For this reason, the increase in enzymatic process efficiency is unavoidable to cut production cost. On this study, we intend to improve efficiency from enzyme with nanoporous material for reusability from cellulose enzyme, while keeping activity and stability from enzyme.

The purpose from this research is to study the use of nanomaterial to improve enzyme stability and the use of nanomaterial to enzyme reusability. There are many factors that influence activity, stability and reusability from cellulase enzyme such as chemical character of surface, particle size from nanoporous material (micron sized: 4-8 micrometer and submicron: 100-300 nm), property of nanoporous will be examined to reduce production cost so it can increase efficiency from enzymatic process.

This research is divided into 4 stages, nanoporous silica synthesis, chemical character modification of surface, enzyme immobilization, and activity, stability and reusability of enzyme measurement. At first stage, cubic mesostucture nanoporous silica (FDU-12) will be synthesized in two different particle size: micron size and submicron size. Then, chemical character modification of surface with organosilane (VTMS: Vinyltrimetoxysilane) in different ratio. Next, enzyme immobilization and measure enzyme activity with: filter paper and CMC methods. Functionalized nanoporous silica product that filled by enzyme is used to convert cellulose into glucose. Finally the optimum condition that give best efficiency to improve activity, stability and reusability from cellulose enzyme will be determined.